



*Start saving energy now.
Contact your local distributor.*

Unifrax Ltd.

T:+44 (0)1744 88 7600

F:+44 (0)1744 88 9916

www.unifrax.com

DESCRIPTION

Fiberfrax Anchor-Loc modules are manufactured from ceramic fibre blanket to provide two standard construction forms, edge-stacked or folded. These prefabricated anchored modules are specifically designed to meet the thermal insulation requirements of industrial furnaces, kilns and heaters. Anchor-Loc modules can be produced with various anchoring systems to enable quick, easy and efficient installation for most lining applications. Available in a wide range of grade, thickness and density combinations, the Fiberfrax Anchor-Loc range offers effective engineered solutions to thermal management problems in many industry sectors.

GENERAL CHARACTERISTICS

Fiberfrax Anchor-Loc modules have the following outstanding characteristics and advantages:

- High temperature stability
- Low thermal conductivity & heat storage
- Resistance to thermal shock & chemical attack
- Lightweight
- Fast installation & selection of attachment designs

TYPICAL APPLICATIONS

Petrochemical

- Furnaces & Fired heaters

Metallurgy

- Heat treatment & Forge furnaces
- Ladle & Soaking pit covers

Ceramic

- Tunnel kilns & Intermittent kilns

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

TYPICAL PRODUCT PARAMETERS

Fiberfrax Anchor-Loc	S	Z	MX
Typical Chemical Analysis (fibre wt. %)			
SiO ₂	53.0 - 58.0	52.0 - 56.0	52.0 - 56.0
Al ₂ O ₃	42.0 - 47.0	28.0 - 32.0	28.0 - 32.0
ZrO ₂	-	14.0 - 18.0	14.0 - 18.0
Fe ₂ O ₃ + TiO ₂	<0.2	<0.2	<0.2
Alkalis	<0.25	<0.25	<0.25
Physical Properties			
Colour	White	White	White
Product Density (kg/m ³)	160 / 170 / 190	160 / 170 / 190	210
Use Limit (°C)*	1200	1350	1420
Classification Temperature (°C)†	1250	1400	1450
Permanent Linear Shrinkage (%) 24 hour soak			
1200 °C	<3.0	-	-
1350 °C	-	<3.0	-
1420 °C	-	-	<3.0

* The maximum continuous use limit temperature for these products depends upon operating and application conditions. For certain applications operational temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office. Where appropriate Physical Properties are measured according to EN 1094-1.

† Based on classification temperature of the fibre in blanket form.

AVAILABILITY (STANDARD TRUCK)

Module Dimensions (mm)			RX2	TL, WL
Length	Width	Thickness	Per Pallet	Per Pallet
300	300	100	264	308
		125	192	224
		150	168	196
		175	144	168
		200	120	140
		225	96	112
		250	96	112
		275	96	112
		300	72	84
		325	72	84
		350	72	84

Other densities, thicknesses / sizes may be available on request subject to minimum order requirements.

Anchor systems available include:

RX2 = Side fixing system: Standard grade AISI 321

TL = Thread-Loc. Centre fixing system: Standard grade AISI 304

WL = Weld-Loc: Standard grade AISI 304

THERMAL CONDUCTIVITY DATA (W/mK)

Mean Temp. (°C)	Density (kg/m ³)			
	160	170	190	210
600	0.16	0.15	0.14	0.13
800	0.20	0.19	0.17	0.16
1000	0.27	0.25	0.22	0.21
1200	0.35	0.33	0.28	0.26

Thermal Conductivity figures are empirical values based on experience.

HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.