Insulfrax® LT Blanket



Start saving energy now. Contact your local distributor.

Unifrax Ltd.

www.unifrax.com

T:+44 (0)1744 88 7600 F:+44

F:+44 (0)1744 88 9916

U-213 ENRev: 4 Jun 13
Page 1 of 2

DESCRIPTION

Insulfrax LT Blanket is the latest addition to our Insulfrax Blanket range. This blanket offers the same benefits as the other Insulfrax blankets but with physical properties enhanced to improve thermal performance and handling. Insulfrax LT Blankets are completely inorganic and so retain their strength, flexibility and thermal properties in many working environments, without the generation of smoke or fumes. Available in a range of density and thickness combinations, Insulfrax LT Blankets can be used in a wide variety of applications and are especially suited to use as high temperature wraps and heat shields.

GENERAL CHARACTERISTICS

Insulfrax LT Blankets products have the following outstanding characteristics:

- Exceptional insulating properties
- High temperature stability (up to 1200°C)
- Resistance to thermal shock
- High tensile strength & resiliency
- Excellent flexibility
- Good sound absorption

TYPICAL APPLICATIONS

- Furnace and kiln linings
- Boiler insulations
- Passive fire protection
- Pipe, duct and chimney insulation
- Heat shields
- Mould wrap insulation

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.



TYPICAL PRODUCT PARAMETERS

		Insulfrax LT Bland	ket	
Typical Chemical Analysis (wt.%)				
SiO ₂		61.0 - 67.0		
CaO		27.0 - 33.0		
MgO	2.5 - 6.5			
AI_2O_3		<1.0		
Fe ₂ O ₃		<0.6		
Physical Properties				
Colour		White		
Classification Temperature (°C) *		1200		
Melting Point (°C)		>1330		
Mean Fibre Diameter (microns)		4.0		
Permanent Linear Shrinkage (%) 24 h	our soak			
1200 °C		1.0		
Density (kg/m³)	96	128	160	
Thermal Conductivity (W/mK)				
Mean Temp.				
200 °C	0.06	0.05	0.05	
400 °C	0.09	0.08	0.08	
600 °C	0.14	0.12	0.11	
800 °C	0.20	0.18	0.15	
1000 °C	0.29	0.25	0.21	
Tensile Strength (kPa)				
	60	80	100	

^{*}Classification Temperature is not a definition of the operational limit of these products, especially when long term physical or dimensional stability is a factor. For certain applications continuous use temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office. Where appropriate Physical Properties data measured according to EN 1094-1. Thermal Conductivity measured in accordance with ASTM C-201.

AVAILABILITY

Thickness (mm)	Density (kg/m³)			Roll Length (m)
	96	128	160	
6	✓	✓		22.00
13	✓	✓	\checkmark	14.64
25	√	✓	✓	7.32
38	✓	✓	\checkmark	5.00
50	✓	✓	√	3.66

Standard roll width is 610mm or 1220mm. Other thicknesses, sizes and densities (e.g. 64 and 80 kg/m^3) are available on request subject to minimum order requirements. Versions with aluminium foil and other coverings are available subject to order.

HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.