



DESCRIPTION

Insulfrax alkaline earth silicate wool provide the basis for the entire family of Insulfrax product forms. As a world leader in the production of alkaline earth silicate wools, Unifrax is able to engineer one of the most comprehensive ranges of fibres available with characteristics optimised to suit a wide variety of applications.

GENERAL CHARACTERISTICS

Insulfrax Bulk and Chopped Fibres have the following outstanding characteristics:

- High temperature stability (up to 1200°C)
- Low thermal conductivity
- Good sound absorption
- Excellent wet forming characteristics

TYPICAL APPLICATIONS

- Loose insulating fill for voids
- Expansion joint packing
- Wet process feedstock
- Textile manufacture

Any new and/or special use of these products, whether or not in an application listed in our literature, must be submitted to our technical department for their prior written approval.

*Start saving energy now.
Contact your local distributor.*

Unifrax Ltd.

T: +44 (0)1744 88 7600

F: +44 (0)1744 88 9916

www.unifrax.com



TYPICAL PRODUCT PARAMETERS

	<i>Insulfrax</i>
Typical Chemical Analysis (fibre wt. %)	
SiO ₂	61.0 - 67.0
CaO	27.0 - 33.0
MgO	2.5 - 6.5
Al ₂ O ₃	< 1.0
Fe ₂ O ₃	< 0.6
Physical Properties	
Colour	White
Melting Point (°C)	>1330
Grade Temperature (°C) *	1200
Mean Fibre Diameter (microns)	3.2

*Grade Temperature is based Classification Temperature of the fibre in blanket form and is not a definition of the operational limit of these products. For certain applications operational temperature limits may be significantly reduced. For assistance or clarification please contact your nearest Unifrax Engineering office. Where appropriate Physical Properties data measured according to EN 1094-1.

BULK FIBRES

Grade	Fibre Coating	Description
S16	None	Regular
S26	Organic Lubricant	Lubricated

CHOPPED FIBRES

Grade	Fibre Coating	Description
S162	None	Fine Chopped
S163	None	Medium Chopped
S164	None	Coarse Chopped

AVAILABILITY

Insulfrax Bulk and Chopped Fibres are available as standard in 20kg polythene bagged bales. Other sizes available on request subject to minimum order requirements.

HANDLING INFORMATION

A Material Safety Data Sheet has been issued describing the health, safety and environmental properties of this product, identifying the potential hazards and giving advice on handling precautions and emergency procedures. This must be consulted and fully understood before handling, storage or use.

Supplied by:

Information contained in this publication is for illustrative purposes only and is not intended to create any contractual obligation. Further information and advice on specific details of the products described should be obtained in writing from a Unifrax Corporation company (Unifrax España, Unifrax France, Unifrax GmbH, Unifrax Italia, Unifrax Limited, Unifrax s.r.o.). Unifrax maintains a continuous programme of product development and reserves the right to change product specifications without prior notice. Therefore, it maintains at all times the responsibility of the customer to ensure that Unifrax materials are suitable for the particular purpose intended. Similarly, insofar as materials not manufactured nor supplied by Unifrax are used in conjunction with or instead of Unifrax materials, the customer should ensure that all technical data and other information relating to such materials has been obtained from the manufacturer or supplier. Unifrax accepts no liability arising from the use of such materials. All sales made by a Unifrax Corporation company are subject to that company's Terms and Conditions of Sale, copies of which are available on request.